



Environmental product declaration

in accordance with ISO 14025 and EN 15804+A2

Industrisement, Brevik - CEM II/A-L 42,5 R eng





The Norwegian EPD Foundation

Owner of the declaration:

Heidelberg Materials Sement Norge AS

Product:

Industrisement, Brevik - CEM II/A-L 42,5 R eng

Declared unit:

1 tonne

This declaration is based on Product Category Rules:

CEN Standard EN 15804:2012+A2:2019 serves as core PCR and EN 16908 is used as PCR Part B EN 16908:2017 Cement and building lime

Program operator:

The Norwegian EPD Foundation

Declaration number:

NEPD-5925-5192-EN

Registration number:

NEPD-5925-5192-EN

Issue date: 31.01.2024

Valid to: 31.01.2029

EPD software:

LCAno EPD generator ID: 295284



General information

Product

Industrisement, Brevik - CEM II/A-L 42,5 R eng

Program operator:

Post Box 5250 Majorstuen, 0303 Oslo, Norway The Norwegian EPD Foundation Phone: +47 23 08 80 00 web: post@epd-norge.no

Declaration number:

NEPD-5925-5192-EN

This declaration is based on Product Category Rules:

CEN Standard EN 15804:2012+A2:2019 serves as core PCR and EN 16908 is used as PCR Part B EN 16908:2017 Cement and building lime

Statement of liability:

The owner of the declaration shall be liable for the underlying information and evidence. EPD Norway shall not be liable with respect to manufacturer information, life cycle assessment data and evidences.

Declared unit:

1 tonne Industrisement, Brevik - CEM II/A-L 42,5 R eng

Declared unit with option:

A1-A3,A4

Functional unit:

General information on verification of EPD from EPD tools:

Independent verification of data, other environmental information and the declaration according to ISO 14025:2010, § 8.1.3 and § 8.1.4. Verification of each EPD is made according to EPD-Norway's guidelines for verification and approval requiring that tools are i) integrated into the company's environmental management system, ii) the procedures for use of the EPD tool are approved by EPD-Norway, and iii) the process is reviewed annually by an independent third party verifier. See Appendix G of EPD-Norway's General Programme Instructions for further information on EPD tools

Verification of EPD tool:

Independent third party verification of the EPD tool, background data and test-EPD in accordance with EPDNorway's procedures and guidelines for verification and approval of EPD tools.

Third party verifier:

Martin Erlandsson, IVL Swedish Res. Inst

(no signature required)

Owner of the declaration:

Heidelberg Materials Sement Norge AS Contact person: Petter Thyholdt Phone: +47 22 87 84 00 e-mail: petter.thyholdt@heidelbergmaterials.com

Manufacturer:

Heidelberg Materials Sement Norge AS Lilleakerveien 2A 0283 Oslo. Norway

Place of production:

Heidelberg Materials Sement Norge prod.site Brevik sementfabrikk Setreveien 2 3950 Brevik, Norway

Management system:

Miljøstyringssystem ISO 14001-sertifisert(S-007) Kvalitetssikriingssystem ISO 9001- sertifisert (S-006)

Organisation no:

934 949 145

Issue date:

31.01.2024

Valid to:

31.01.2029

Year of study:

2022

Comparability:

EPD of construction products may not be comparable if they not comply with EN 15804 and seen in a building context.

Development and verification of EPD:

The declaration is created using EPD tool lca.tools ver EPD2022.03, developed by LCA.no. The EPD tool is integrated in the company's management system, and has been approved by EPD Norway.

Developer of EPD: Ingrid Vik Jondahl

Reviewer of company-specific input data and EPD: Petter Thyholdt

Approved:

Håkon Hauan, CEO EPD-Norge



Product

Product description:

Industrisement is a special cement adapted to Norwegian construction practice for winter work. The cement makes it possible to carry out casting work during the winter in Norway in a rational and economical way.

With its rapid strength development, it is also suitable for use in the production of concrete elements and concrete products.

Product specification

Portland-limestone cement

| Materials | Value | Unit |
|------------------|-------|------|
| Klinker | 84,6 | % |
| Kalksteinsfiller | 10 | % |
| Gips | 5,4 | % |

Technical data:

CEM II/A-L 42,5 R

Further information is available at www.sement.heidelbergmaterials.no

Market:

Norway, Iceland

Reference service life, product

Depending on the area of use

Reference service life, building or construction works

LCA: Calculation rules

Declared unit:

1 tonne Industrisement, Brevik - CEM II/A-L 42,5 R eng

Cut-off criteria:

All major raw materials and all the essential energy is included. The production processes for raw materials and energy flows with very small amounts (less than 1%) are not included. These cut-off criteria do not apply for hazardous materials and substances.

Allocation

The allocation is made in accordance with the provisions of EN 15804. Incoming energy and water and waste production in-house is allocated equally among all products through mass allocation. The recycling process and transportation of the material is allocated to this analysis.

Data quality:

Specific data for the product composition are provided by the manufacturer. The data represent the production of the declared product and were collected for EPD development in the year of study. Background data is based on EPDs according to EN 15804 and different LCA databases. The data quality of the raw materials in A1 is presented in the table below.

| Materials | Source | Data quality | Year |
|------------------------|---------------|--------------|------|
| Additives | ecoinvent 3.6 | Database | 2019 |
| Binder | ecoinvent 3.6 | Database | 2019 |
| Raw materials, Mineral | LCA.no | Database | 2021 |
| Raw materials, Mineral | Supplier | Project EPD | 2021 |
| SCM | LCA.no | Database | 2021 |
| Waste products | LCA.no | Database | 2021 |




System boundaries (X=included, MND=module not declared, MNR=module not relevant)


| P | roduct stag | ge | | uction ion stage | Use stage | | End of life stage | | | Beyond the system boundaries | | | | | | |
|------------------|-------------|---------------|-----------|---------------------|-----------|-------------|-------------------|-------------|-------------------------|------------------------------|--------------------------|-----------------------------------|-----------|---------------------|----------|--|
| Raw materials | Transport | Manufacturing | Transport | Assembly | Use | Maintenance | Repair | Replacement | Refu <i>r</i> b ishment | Operational energy use | Operational water use | De- construction demolition | Transport | Waste processing | Disposal | Reuse-Recovery- Recycling-potential |
| A1 | A2 | A3 | A4 | A5 | B1 | B2 | В3 | B4 | B5 | В6 | В7 | C1 | C2 | C3 | C4 | D |
| Χ | Χ | Х | Χ | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND | MND |

System boundary:

From rawmaterial extraction to market



- 1. Uttak av kalkstein fra gruve og dagbrudd
- 2. Knusing av kalkstein
- 3. Maling av kalkstein og tilsetningstoffer til råmel
- 4. Siloer for lagring og homogenisering
- Brenning av klinker i roterende ovn der materialene når en temperatur på 1450°C
- 6. Siloer for lagring av klinker
- Maling av klinker med gips og andre tilsetninger for produksjon av sement
- 8. Tilsetning av jernsulfat
- 9. Lagring og utsendelse av sementen



Additional technical information:



LCA: Scenarios and additional technical information

The following information describe the scenarios in the different modules of the EPD.

| Transport from production place to user (A4) | Capacity utilisation (incl. return) % | Distance (km) | Fuel/Energy Consumption | Unit | Value (Liter/tonne) |
|--|--|---------------|-------------------------|-------|------------------------|
| Ship, Cement boat | 50,0 % | 163 | 0,005 | l/tkm | 0,81 |



LCA: Results

The LCA results are presented below for the declared unit defined on page 2 of the EPD document.

| Environmental | impact | | | |
|----------------------|----------------------------------|------------------------|----------|----------|
| | Indicator | Unit | A1-A3 | A4 |
| | GWP-total | kg CO ₂ -eq | 6,58E+02 | 2,50E+00 |
| | GWP-fossil | kg CO ₂ -eq | 6,58E+02 | 2,50E+00 |
| | GWP-biogenic | kg CO ₂ -eq | 1,35E-01 | 5,10E-04 |
| | GWP-luluc | kg CO ₂ -eq | 2,47E-02 | 9,65E-04 |
| ٥ | ODP | kg CFC11 -eq | 3,52E-06 | 4,88E-07 |
| Œ | АР | mol H+ -eq | 5,96E-01 | 7,54E-02 |
| & | EP-FreshWater | kg P -eq | 4,14E-03 | 6,99E-06 |
| | EP-Marine | kg N -eq | 1,52E-01 | 1,69E-02 |
| | EP-Terrestial | mol N -eq | 1,99E+00 | 1,90E-01 |
| | POCP | kg NMVOC -eq | 4,53E-01 | 4,92E-02 |
| | ADP-minerals&metals ¹ | kg Sb-eq | 4,30E-04 | 1,06E-05 |
| | ADP-fossil ¹ | MJ | 1,01E+03 | 3,22E+01 |
| <u>%</u> | WDP ¹ | m ³ | 9,65E+03 | 7,17E+00 |

GWP-total = Global Warming Potential total; GWP-fossil = Global Warming Potential fossil fuels; GWP-biogenic = Global Warming Potential biogenic; GWP-luluc = Global Warming Potential land use and land use change; ODP = Depletion potential of the stratospheric ozone layer; AP = Acidification potential, Accumulated Exceedance; EP-freshwater = Eutrophication potential, fraction of nutrients reaching freshwater end compartment: EP-marine = Eutrophication potential, fraction of nutrients reaching marine end compartment; EP-terrestrial = Eutrophication potential, Accumulated Exceedance; POCP = Formation potential of tropospheric ozone; ADP-minerals&metals = Abiotic depletion potential for non-fossil resources; ADP-fossil = Abiotic depletion for fossil resources potential; WDP = Water (user) deprivation potential, deprivation-weighted water consumption

Remarks to environmental impacts

The parameter GWP (A1-A3) includes 142.0 kg CO2-eq. from the combustion of alternative fossil fuels during clinker production. In accordance with the "polluter pays" principle / EN 15804 /, the emissions will be added to the production system that caused the waste. In this EPD, the CO2 contribution from alternative fossil fuels has not been deducted. This is to be able to compare calculated global warming from cement regardless of the status of the waste in different countries

[&]quot;Reading example: 9,0 E-03 = 9,0*10-3 = 0,009"

^{*}INA Indicator Not Assessed

^{1.} The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experienced with the indicator



| Additional environmental impact indicators | | | | | | | |
|--|---------------------|-------------------|----------|----------|--|--|--|
| | Indicator | Unit | | A4 | | | |
| | PM | Disease incidence | 3,49E-06 | 0,00E+00 | | | |
| (in) | IRP ² | kgBq U235 -eq | 1,91E+00 | 1,40E-01 | | | |
| 43 | ETP-fw ¹ | CTUe | 1,23E+04 | 1,67E+01 | | | |
| 40.* *** <u>*</u> | HTP-c ¹ | CTUh | 1,60E-08 | 0,00E+00 | | | |
| ₩ <u></u> | HTP-nc ¹ | CTUh | 4,38E-07 | 0,00E+00 | | | |
| | SQP ¹ | dimensionless | 2,27E+02 | 4,11E+00 | | | |

PM = Particulate Matter emissions; IRP = Ionizing radiation – human health; ETP-fw = Eco toxicity – freshwater; HTP-c = Human toxicity – cancer effects; HTP-nc = Human toxicity – non cancer effects; SQP = Potential Soil Quality Index (dimensionless)

[&]quot;Reading example: 9,0 E-03 = 9,0*10-3 = 0,009"

^{*}INA Indicator Not Assessed

^{1.} The results of this environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experienced with the indicator

^{2.} This impact category deals mainly with the eventual impact of low dose ionizing radiation on human health of the nuclear fuel cycle. It does not consider effects due to possible nuclear accidents, occupational exposure nor due to radioactive waste disposal in underground facilities. Potential ionizing radiation from the soil, from radon and from some construction materials is also not measured by this indicator.



| Resource use | | | | |
|--------------|-----------|----------------|----------|----------|
| | Indicator | Unit | A1-A3 | A4 |
| i i | PERE | MJ | 7,19E+02 | 1,59E-01 |
| | PERM | MJ | 0,00E+00 | 0,00E+00 |
| ್ಕೈ | PERT | MJ | 7,19E+02 | 1,59E-01 |
| | PENRE | MJ | 1,01E+03 | 3,22E+01 |
| | PENRM | MJ | 0,00E+00 | 0,00E+00 |
| IA | PENRT | MJ | 1,01E+03 | 3,22E+01 |
| <u></u> | SM | kg | 5,47E+00 | 0,00E+00 |
| | RSF | MJ | 1,20E+03 | 6,11E-03 |
| | NRSF | MJ | 1,39E+03 | 4,18E-02 |
| % | FW | m ³ | 5,35E+00 | 9,08E-04 |

PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; PERM = Use of renewable primary energy resources used as raw materials; PERT = Total use of renewable primary energy resources; PENRE = Use of non renewable primary energy resources used as raw materials; PENRM = Use of non renewable primary energy resources; SM = Use of secondary materials; PENRM = Use of renewable secondary fuels; NRSF = Use of non-renewable secondary fuels; FW = Net use of fresh water

[&]quot;Reading example: 9,0 E-03 = 9,0*10-3 = 0,009" *INA Indicator Not Assessed



| End of life - Waste | | | | | | | |
|---------------------|------|------|----------|----------|--|--|--|
| Indicator | | Unit | A1-A3 | A4 | | | |
| | HWD | kg | 8,78E-02 | 1,03E-03 | | | |
| Û | NHWD | kg | 5,37E+00 | 4,55E-02 | | | |
| | RWD | kg | 1,93E-03 | 2,28E-04 | | | |

HWD = Hazardous waste disposed; NHWD = Non-hazardous waste disposed; RWD = Radioactive waste disposed

"Reading example: 9,0 E-03 = 9,0*10-3 = 0,009" *INA Indicator Not Assessed

| End of life - Output flow | | | | | | | |
|---------------------------|-----|------|----------|----------|--|--|--|
| Indicator | | Unit | A1-A3 | A4 | | | |
| @> | CRU | kg | 0,00E+00 | 0,00E+00 | | | |
| ⇔> | MFR | kg | 1,63E-02 | 0,00E+00 | | | |
| DØ | MER | kg | 1,85E-04 | 0,00E+00 | | | |
| ₹ \$ | EEE | MJ | 1,13E-03 | 0,00E+00 | | | |
| DÐ | EET | MJ | 1,70E-02 | 0,00E+00 | | | |

CRU = Components for re-use; MFR = Materials for recycling; MER = Materials for energy recovery; EEE = Exported energy electrical; EET = Exported energy thermal

"Reading example: 9,0 E-03 = 9,0*10-3 = 0,009" *INA Indicator Not Assessed

| Biogenic Carbon Content | | | | | | |
|-------------------------|---------------------|--|--|--|--|--|
| Unit | At the factory gate | | | | | |
| kg C | 0,00E+00 | | | | | |
| kg C | 0,00E+00 | | | | | |
| | kg C | | | | | |

Note: 1 kg biogenic carbon is equivalent to 44/12 kg CO2



Additional requirements

Greenhouse gas emissions from the use of electricity in the manufacturing phase

National production mix from import, low voltage (production of transmission lines, in addition to direct emissions and losses in grid) of applied electricity for the manufacturing process (A3).

| Electricity mix | Data source | Amount | Unit |
|---------------------------|---------------|--------|--------------|
| Electricity, Norway (kWh) | ecoinvent 3.6 | 24,33 | g CO2-eg/kWh |

Dangerous substances

The product contains no substances given by the REACH Candidate list.

Indoor environment

Additional Environmental Information

| Additional environmental impact indicators required in NPCR Part A for construction products | | | | | |
|--|------------------------|----------|----------|--|--|
| Indicator | Unit | A1-A3 | A4 | | |
| GWPIOBC | kg CO ₂ -eq | 6,55E+02 | 2,50E+00 | | |

GWP-IOBC: Global warming potential calculated according to the principle of instantaneous oxidation. In order to increase the transparency of biogenic carbon contribution to climate impact, the indicator GWP-IOBC is required as it declares climate impacts calculated according to the principle of instantaneous oxidation. GWP-IOBC is also referred to as GWP-GHG in context to Swedish public procurement legislation.



Bibliography

ISO 14025:2010 Environmental labels and declarations - Type III environmental declarations - Principles and procedures.

ISO 14044:2006 Environmental management - Life cycle assessment - Requirements and guidelines.

EN 15804:2012 + A2:2019 Environmental product declaration - Core rules for the product category of construction products.

ISO 21930:2017 Sustainability in buildings and civil engineering works - Core rules for environmental product declarations of construction products.

ecoinvent v3, Allocation, cut-off by classification, Swiss Centre of Life Cycle Inventories.

Iversen et al., (2021) eEPD v2021.09 Background information for EPD generator tool system verification, LCA.no report number: 07.21 Vold et al, (2022) EPD generator for CEN PCR EN 16908:2017 Cement and building lime - Background information for PCR application and LCA data, LCA.no report number: 01.22.

NPCR Part A: Construction products and services. Ver. 2.0. April 2021, EPD-Norge.

CEN PCR EN 16908:2017 Cement and building lime

| and narway | Program operator and publisher | | Phone: | +47 23 08 80 00 |
|-------------------------|---|---------|------------------|-------------------------|
| © epd-norway | The Norwegian EPD Foundation | | e-mail: | post@epd-norge.no |
| Global Program Operator | Post Box 5250 Majorstuen, 0303 Oslo, Norway | | web: | www.epd-norge.no |
| Heidelberg Materials | Owner of the declaration: | Phone: | +47 22 87 84 0 | 0 |
| | Heidelberg Materials Sement Norge AS | e-mail: | petter.thyholdt@ | heidelbergmaterials.com |
| | Lilleakerveien 2A, 0283 Oslo | web: | www.sement.he | idelbergmaterials.no |
| LCA ^N | Author of the Life Cycle Assessment | | Phone: | +47 916 50 916 |
| | LCA.no AS | | e-mail: | post@lca.no |
| | Dokka 6B, 1671 | | web: | www.lca.no |
| (LCA) | Developer of EPD generator | | Phone: | +47 916 50 916 |
| | LCA.no AS | | e-mail: | post@lca.no |
| .no | Dokka 6B,1671 Kråkerøy | | web: | www.lca.no |
| ECO PLATFORM | ECO Platform | | web: | www.eco-platform.org |
| VERIFIED | ECO Portal | | web: | ECO Portal |
| | | | | |