

PRODUCT DATA SHEET

NORCEM MICRO

February 2018

The cement is produced of fine grinded Norcem Industrisement that meets the demands in NS-EN 197-1:2011 to a Portland cement CEM I 52,5R.

Fineness (Blaine kg/m ²)		720	
Specific weight (kg/dm ³)		3.13	
Soundness (mm)		1	≤ 10
Initial setting time (min)		100	≥ 45
Sulfat (% SO ₃)		≤ 4.0	≤ 4.0
Chloride (%Cl ⁻)		≤ 0.085	≤ 0.10
Water soluble chromium (ppm Cr ⁺⁶) ¹		≤ 2	≤ 2 ¹⁾
Alkalies (Na ₂ O ekv)		1.3	
Clinker (%)		96	95-100
Minor add. components (%)		4	0-5

1) According to EU-regulation REACH Annex XVII point 47 Chromium VI-compounds.

NORCEM
HEIDELBERGCEMENT Group

Norcem AS, P.O.Box 142, Lilleaker, N-0216 Oslo
Phone: 0047 22 87 84 00 firmapost@norcem.no www.norcem.no